

H-K2			500660			n <sub>d</sub> = 1.500470		v <sub>d</sub> = 66.02		n <sub>F</sub> - n <sub>C</sub> = 0.007581												
						n <sub>e</sub> = 1.502279		v <sub>e</sub> = 65.83		n <sub>F'</sub> - n <sub>C'</sub> = 0.007630												
<b>折射率 Refractive Index</b>			<b>相对部分色散 Relative Partial Dispersions</b>				<b>内部透射率 Internal Transmittance T</b>															
	λ (nm)		P <sub>s,t</sub>	0.3182	P' <sub>s,t</sub>	0.3161	λ (nm)	τ (5mm)	τ (10mm)													
n <sub>2325.42</sub>	2325.42	1.473266	P <sub>C,s</sub>	0.5676	P' <sub>C',s</sub>	0.6132	2400	0.912	0.832													
n <sub>1970.09</sub>	1970.09	1.479079	P <sub>d,C</sub>	0.3087	P' <sub>d,C'</sub>	0.2574	2200	0.936	0.875													
n <sub>1529.58</sub>	1529.58	1.485081	P <sub>e,d</sub>	0.2386	P' <sub>e,d</sub>	0.2371	2000	0.989	0.978													
n <sub>1060.0</sub>	1060.0	1.490810	P <sub>g,F</sub>	0.5323	P' <sub>g,F'</sub>	0.4731	1800	0.996	0.992													
n <sub>t</sub>	1013.98	1.491415	P <sub>i,h</sub>	0.7404	P' <sub>i,h</sub>	0.7356	1600	0.999	0.998													
n <sub>s</sub>	852.11	1.493827	<b>异常色散 Abnormal Dispersions</b>				1400	0.990	0.979													
n <sub>r</sub>	706.52	1.496775					ΔP <sub>C,t</sub>	0.0284	ΔP <sub>C,s</sub>	0.0098	1200	0.999	0.998									
n <sub>C</sub>	656.27	1.498130	ΔP <sub>F,e</sub>	-0.0010	ΔP <sub>g,F</sub>	-0.0010	1060	0.999	0.998													
n <sub>C'</sub>	643.85	1.498506	<b>着色度 Color Code</b>				1000	0.999	0.998													
n <sub>He-Ne</sub>	632.8	1.498856					λ <sub>80</sub> /λ <sub>5</sub>	310/280			950	0.999	0.998									
n <sub>D</sub>	589.29	1.500402	λ <sub>70</sub> /λ <sub>5</sub>				900	0.999	0.998													
n <sub>d</sub>	587.56	1.500470	<b>热性质 Thermal Properties</b>				850	0.999	0.998													
n <sub>e</sub>	546.07	1.502279					T <sub>g</sub> (°C)	556			800	0.999	0.998									
n <sub>F</sub>	486.13	1.505711	T <sub>s</sub> (°C)	648			700	0.999	0.997													
n <sub>F'</sub>	479.99	1.506136	T <sub>10</sub> <sup>14.5</sup> (°C)	508			650	0.998	0.996													
n <sub>g</sub>	435.83	1.509746	T <sub>10</sub> <sup>13</sup> (°C)	557			600	0.998	0.996													
n <sub>h</sub>	404.66	1.513067	T <sub>10</sub> <sup>7.6</sup> (°C)	759			550	0.998	0.997													
n <sub>i</sub>	365.01	1.518680	α <sub>-30/70</sub> (10 <sup>-7</sup> /K)	55			500	0.998	0.996													
n <sub>313.18</sub>	313.18	1.529927	α <sub>100/300</sub> (10 <sup>-7</sup> /K)	65			480	0.998	0.995													
n <sub>302.15</sub>	302.15	1.533218	λ[W/(m·K)]				460	0.997	0.995													
<b>色散公式常数 Constants of Dispersion Formula</b>			<b>化学性质 Chemical Properties</b>				<b>机械性质 Mechanical Properties</b>															
												K <sub>1</sub>	9.51357962E-01		Grade		H <sub>k</sub> (10 <sup>7</sup> Pa)		534			
												L <sub>1</sub>	1.12894891E-02		D <sub>w</sub>	2		F <sub>A</sub>		83		
												K <sub>2</sub>	9.69614738E-01		D <sub>A</sub>	1		E (10 <sup>7</sup> Pa)		7249		
												L <sub>2</sub>	9.91744348E+01		CR	1		G (10 <sup>7</sup> Pa)		3008		
												K <sub>3</sub>	2.73207194E-01		RC(S)	1		μ		0.204		
												L <sub>3</sub>	-2.45665699E-03		RA(S)	1		B (10 <sup>-12</sup> /Pa)		3.12		
<b>折射率温度系数常数 Constants of dn/dt</b>			<b>折射率温度系数 Temperature Coefficients of Refractive Index</b>				<b>其他性质 Other Properties</b>															
												温度范围 (°C) Range of Temperature		dn/dt relative(10 <sup>-6</sup> /°C)					ρ (g/cm <sup>3</sup> )		2.42	
														t	C'	d	e	F'	g	<b>备注 Remarks</b>		
												-60~-40	2.4	2.8	2.8	2.8	3.1	3.3				
												-40~-20	2.6	2.8	2.9	3.1	3.2	3.4				
												-20~0	2.6	2.9	3.0	3.1	3.3	3.5				
												0~20	2.7	3.0	3.1	3.2	3.5	3.8				
												20~40	3.1	3.3	3.4	3.6	3.7	4.1				
												40~60	3.2	3.5	3.7	3.8	4.2	4.3				
												60~80	3.2	3.6	3.8	3.9	4.3	4.3				
												80~100	3.4	3.8	4.0	3.9	4.3	4.4				
100~120	3.5	4.0	4.1	4.2	4.3	4.5																
120~140	3.9	4.2	4.3	4.5	4.5	4.8																