

H-K9LGT			517642				n _d = 1.516800		v _d = 64.20		n _F - n _C = 0.008050	
							n _e = 1.518721		v _e = 63.98		n _{F'} - n _{C'} = 0.008107	
折射率 Refractive Index			相对部分色散 Relative Partial Dispersions				内部透射率 Internal Transmittance T					
	λ (nm)		P _{s,t}	0.3071	P' _{s,t}	0.3049	λ (nm)	τ (5mm)	τ (10mm)			
n _{2325.42}	2325.42	1.489640	P _{C,s}	0.5588	P' _{C',s}	0.6038	2400	0.851	0.725			
n _{1970.09}	1970.09	1.495235	P _{d,C}	0.3073	P' _{d,C'}	0.2562	2200	0.888	0.788			
n _{1529.58}	1529.58	1.501060	P _{e,d}	0.2386	P' _{e,d}	0.2370	2000	0.954	0.911			
n _{1060.0}	1060.0	1.506743	P _{g,F}	0.5359	P' _{g,F'}	0.4761	1800	0.980	0.960			
n _t	1013.98	1.507356	P _{i,h}	0.7499	P' _{i,h}	0.7447	1600	0.994	0.988			
n _s	852.11	1.509828	异常色散 Abnormal Dispersions				1400	0.989	0.978			
n _r	706.52	1.512901					ΔP _{C,t}	0.0171	ΔP _{C,s}	0.0052	1200	0.999
n _C	656.27	1.514326	ΔP _{F,e}	-0.0006	ΔP _{g,F}	-0.0005	1060	0.999	0.998			
n _{C'}	643.85	1.514723	着色度 Color Code				1000	0.999	0.998			
n _{He-Ne}	632.8	1.515092					λ ₈₀ /λ ₅	310/275		950	0.999	0.998
n _D	589.29	1.516728	λ ₇₀ /λ ₅			900	0.999	0.998				
n _d	587.56	1.516800	热性质 Thermal Properties				850	0.999	0.998			
n _e	546.07	1.518721					T _g (°C)	560		800	0.999	0.998
n _F	486.13	1.522376	T _s (°C)	620		700	0.999	0.998				
n _{F'}	479.99	1.522830	T ₁₀ ^{14.5} (°C)	511		650	0.999	0.998				
n _g	435.83	1.526690	T ₁₀ ¹³ (°C)	547		600	0.999	0.998				
n _h	404.66	1.530251	T ₁₀ ^{7.6} (°C)	714		550	0.999	0.998				
n _i	365.01	1.536288	α _{-30/70} (°C)(10 ⁻⁷ /K)	76		500	0.999	0.998				
n _{313.18}	313.18	1.548455	α _{100/300} (°C)(10 ⁻⁷ /K)	95		480	0.999	0.998				
n _{302.15}	302.15	1.552035	λ[W/(m·K)]			460	0.999	0.998				
色散公式常数 Constants of Dispersion Formula			化学性质 Chemical Properties				440	0.999	0.998			
							K ₁	6.14555251E-01		Grade	420	0.999
L ₁	1.45987884E-02		D _w	3		400	0.999	0.998				
K ₂	6.56775017E-01		D _A	1		390	0.999	0.998				
L ₂	2.87769588E-03		CR	2		380	0.999	0.998				
K ₃	1.02699346E+00		RC(S)	1		370	0.999	0.998				
L ₃	1.07653051E+02		RA(S)	1		360	0.999	0.998				
折射率温度系数常数 Constants of dn/dt			机械性质 Mechanical Properties				350	0.997	0.994			
							D ₀	-1.04E-06		H _k (10 ⁷ Pa)	595	
D ₁	1.48E-08		折射率温度系数 Temperature Coefficients of Refractive Index				330	0.987	0.975			
D ₂	-5.17E-11						dn/dt relative(10 ⁻⁶ /°C)		320	0.972	0.944	
E ₀	3.85E-07		温度范围 (°C)	t	C'	d	e	F'	g	H _A	100	
E ₁	4.55E-10		-60~-40	0.9	1.1	1.2	1.3	1.6	1.9	E (10 ⁷ Pa)	7920	
λ _{TK} (μm)	0.211		-40~-20	0.9	1.2	1.3	1.4	1.7	1.9	G (10 ⁷ Pa)	3270	
其他性质 Other Properties			0~-20	1.0	1.3	1.4	1.4	1.8	1.9	μ	0.211	
			20~40	1.0	1.4	1.5	1.5	1.8	2.0	B (10 ⁻¹² /Pa)	2.70	
备注 Remarks			40~60	1.2	1.5	1.6	1.7	1.9	2.2			
			60~80	1.3	1.6	1.6	1.8	2.1	2.3			
			80~100	1.1	1.4	1.5	1.7	2.1	2.3			
			100~120	1.1	1.4	1.5	1.7	2.1	2.4			
			120~140	1.1	1.6	1.8	1.9	2.2	2.7			